



Sendust

P/N	Dimensions(mm)						Path Length (cm)	Cross section Area(cm ²)	AL value (nH/n ²)±12%				
	A	B	C	D(min)	E	F			26μ, B	40μ, J	60μ, C	75μ, D	90μ, E
2014 EQ	20.5	14	8.1	8.8	18	5.7	4.52	0.608	44	68			
2014 EQ	20.5	14	10.1	8.8	18	7.7	5.32	0.608	37	57			
2619 EQ	26.5	19	10.1	12	22.6	6.8	5.47	1.198	72	110			
2619 EQ	26.5	19	12.4	12	22.6	9.1	6.39	1.198	61	94			
3222 EQ	32	22	10.3	13.5	27.6	6.6	6.03	1.523	83	127			
3222 EQ	32	22	15.2	13.5	27.6	11.5	7.99	1.523	62	96			
3626 EQ	36	26	17.4	14.4	32	13.4	9.47	1.808	62	96			
3626 EQ	36	26	17.4	14.4	32	13.4	9.47	1.808	57	88			
4128 EQ	41.5	28	19.9	14.9	36.5	15.4	11.52	1.997	68	105			
4128 EQ	41.5	28	19.9	14.9	36.5	15.4	11.52	1.997	57	87			
5032 EQ	50	32	25	20	44	19.5	13.34	3.141	90	139			
5032 EQ	50	32	25	20	44	19.5	13.34	3.141	77	118			